

- LEXAN 920 701 -

PROPERTIES	UNIT	TEST METHOD	VALUES
<u>Physical</u>			
unreinforced			
Density	g/cm ³	ISO 1183	1.20
Coefficient of thermal expansion in flow direction CTE (23°C-60°C)	1/°C	ASTM D696	7-10 ⁻⁵
Water absorption at saturation at 23°C	%	ISO 62	0.35
<u>Mechanical</u>			
Tensile stress - at yield (at break) at 50 mm/min	MPa	ISO 527	63 (60)
Tensile strain - at yield (at break) at 50 mm/min	%	ISO 527	6 (85)
Tensile modulus at 1mm/min	MPa	ISO 527	2350
Flexural stress at yield (at break) at 2 mm/min	MPa	ISO 178	- (-)
Flexural modulus at 2 mm/min	MPa	ISO 178	2300
Hardness H 358/30	MPa	ISO 2039-1	98
Abrasion resistance Taber, CS-17, 1 kg	mg/1000cy	GE	10
Impact Izod notched at +23°C (- 30°C)	kJ/m ²	ISO 180-1A	9 (7)
<u>Thermal</u>			
Vicat A/50 10N (method A) at 50°C/h	°C	ISO 306	-
Vicat B/50 50N (method B) at 50°C/h	°C	ISO 306	140
HDT / Ae at 1,80 MPa	°C	ISO 75/Ae	122
HDT / Be at 0,45 MPa	°C	ISO 75/Be	133
Relative Temperature Index RTI – electrical properties	°C	UL746B	130
Relative Temperature Index RTI – mechanical properties with impact	°C	UL746B	120
UL 94 rating flame class rating / at mm thickness	Class / mm	UL94	V0/1.04
Limited Oxygen Index- LOI	%	ASTM D2863	35
<u>Electrical</u>			
Dielectric strength at 3,2 mm	kV/mm	ASTM D149	17
Surface resistivity	Ohm	ASTM D257	>10 ¹⁵
Volume resistivity	Ohm,cm	ASTM D257	>10 ¹⁵
Dielectric constant at 50 Hz	-	ASTM D150	3.0
Dielectric constant at 1 MHz	-	ASTM D150	2.9
Dissipation factor at 50 Hz	-	ASTM D150	0.001
Dissipation factor at 1 MHz	-	ASTM D150	0.01

The values indicated are it with titles codes and do not engage to in no case the responsibility for company PHT



PLASTIQUES HAUTES TECHNOLOGIES
 ZA de Malvaisin - 58 rue du Vercors – 38240 LE VERSOUD
 Tél (33) 04 76 776 990 - Fax (33) 04 76 776 994